


## 鉛吸着性能について

鉛吸着試験 (吸着材 1g)

吸着時間(H)	溶液量(ml)	試料(g)	平衡濃度 (mg/L)	吸着量 (mg/g)
0	100	1.0	1.096	0.000
10min	100	1.0	0.336	0.076
30min	100	1.0	0.163	0.093
1	100	1.0	0.099	0.100
4	100	1.0	0.038	0.106
10	100	1.0	0.026	0.107
24	100	1.0	0.010	0.109



1. 鉛吸着試験 (吸着材 2g)

吸着時間(H)	溶液量(ml)	試料(g)	平衡濃度 (mg/L)	吸着量 (mg/g)
0	100	2.0	1.096	0.000
10min	100	2.0	0.235	0.043
30min	100	2.0	0.126	0.049
1	100	2.0	0.072	0.051
4	100	2.0	0.039	0.053
8	100	2.0	0.021	0.054
24	100	2.0	0.008	0.054

